



Technical Data for SLS Arctic NLGI #0 Grade Extreme Pressure Grease

Test	Method	Test Data
SLS Arctic EP #0		
NLGI Grade	NLGI	#0
Thickener Type	-	Lithium
Penetration @ 77F W60	ASTM D-217	370
4-ball EP, weld point, kg.	ASTM D-2596	800
4-ball EP, LWI	ASTM D-2596	150
Timken OK Load (lbs.)	ASTM D-2509	60
Mobility @ 60 F (g/min)	US Steel	3,200
Block on Ring (600lbs/300rpm/1hr)	ASTM D-2714	10,000 psi